Silhouette

SPX Motion Adjustment Instructions



# HOW TO ADJUST BRIDGE:

• Use air heater with small cone *NOTE: do not overheat plastic parts!* 

- Warm bridge carefully until SPX loses tension (approx 176 F)
  - Form it at room temperature
  - Keep position until bridge has cooled down



## HOW TO ADJUST TRIM:

- Fix trim with assembly pliers (pic 1)
  - Use air heater with small cone

#### NOTE: do not overheat plastic parts or ophthalmic lenses!

- Warm up carefully until SPX loses tension (approx 176° F)
- Form manually when SPX component becomes soft (pic 2)
  - Keep in position until trim has cooled down



#### HOW TO DETACH TEMPLE:

Position round stick (1.5-2 mm diameter) close to the hinge
Fold the temple and press together with thumb





SPX Motion Adjustment Instructions (continued)



### HOW TO ADJUST TEMPLE:





Warm up temple carefully (pic 1)
Gently bend curve(pic 2)

# HOW TO ADJUST THE INCLINATION OF THE TEMPLE:

- Disassemble temple with round stick: (1.5-2mm diameter (pic 1))
  - $\bullet$  Fix trim with assembly pliers





